

**Docket No.:** H-508

***APPLICATION***  
***FOR***  
***UNITED STATES LETTERS PATENT***

**Title:** A PROCESS FOR FABRICATING  
THREE-DIMENSIONAL SOLIDS

**Inventors:** Joshua Browning  
Anthony Browning

# A PROCESS FOR FABRICATING THREE-DIMENSIONAL SOLIDS

## Field of the Invention:

5 *Sub A 1* The present invention relates to manufacturing processes and articles made by these processes and, more particularly, to a thermoforming method of fabricating three-dimensional solids, "solid surface" materials and acrylics that have a seamless depression or projection capable of holding a liquid and that simulate natural materials, such as stone, granite, or marble.

## BACKGROUND OF THE INVENTION

15 *Sub A 2* In recent times, the use of artificial stone materials for kitchen counter-tops, basins, tubs, and other fixtures has become very popular with contractors and property owners alike. These materials have the look of granite, marble and other expensive stone materials, but are less costly to fabricate and shape. These artificial stone materials usually  
20 comprise acrylic and acrylic/alumina trihydrate (Wilsonart®,

Gibraltar®, SSV™, DuPont Corian®), and are also known in the trade as "solid surface materials".

57 Sub A<sup>3</sup> In the manufacture of bowls, tubs, counter-tops, and basins of artificial stone-like materials, some manufacturers laminate or chemically weld multiple pieces of "solid surface" sheet stock together, and then machine the pieces to the desired shape. Some manufacturers mold "solid surface" material using two-piece (male/female) molds to create a basic form, and then cut and splice pieces to the deformed shape to achieve the depth and size that they ultimately desire. These methods require more labor and machinery to finish the surfaces, such as sanding the laminated or welded item, and therefore are more time, labor, and material intensive. The intensive nature of these artificial materials has kept the cost of the end products high.

The present invention features a low-cost, thermoforming process that is used to make three dimensional "solid surface" bowls, shower pans, trays, kitchen countertops, and basins. The inventors have discovered that thermoforming is a cost effective method for overcoming the prior art manufacturing limitations of these materials. The inventive process uses a flat, rigid sheet of "solid surface" product

that is heated to a uniform temperature to make it malleable. The material is then placed over a female or male mold and formed to a predetermined shape utilizing vacuum. The heated material is allowed to conform to the mold shape without substantial restraint, until most of the desired deformity is achieved. At that point, movement of the material becomes restricted; the balance of the desired deformity is achieved through stretching. The manufactured component is then allowed to cool in its restrained position, until rigid.

This procedure produces a flange, which provides a point at which, for example, the bowl/shower pan can subsequently be chemically welded in either a convex or concave position. After cooling, the material is removed from the mold and chemically welded to a countertop or curb assembly, in either a horizontal or a vertical plane. A supporting plate is welded at the desired drain location. A drain hole is then machined at the drain location to accommodate the drain hardware.

The inventive process allows formation of a shower base, sink, bowl, or other fixture in one piece, which can retain its shape without losing its strength and integrity. Most particularly in the case of a

shower base or tub, further strengthening can be achieved using polyurethane foam. The polyurethane foam can be poured or sprayed onto the "solid surface" material.

5           The inventive method is unique in that no other current process can fabricate "solid surface" fixtures in one piece using a vacuum and producing a flanged, seamless cost efficient fixture.

#### SUMMARY OF THE INVENTION

10  
15  
20  
25  
30  
35  
40  
45  
50  
55  
60  
65  
70  
75  
80  
85  
90  
95  
100  
105  
110  
115  
120  
125  
130  
135  
140  
145  
150  
155  
160  
165  
170  
175  
180  
185  
190  
195  
200  
205  
210  
215  
220  
225  
230  
235  
240  
245  
250  
255  
260  
265  
270  
275  
280  
285  
290  
295  
300  
305  
310  
315  
320  
325  
330  
335  
340  
345  
350  
355  
360  
365  
370  
375  
380  
385  
390  
395  
400  
405  
410  
415  
420  
425  
430  
435  
440  
445  
450  
455  
460  
465  
470  
475  
480  
485  
490  
495  
500  
505  
510  
515  
520  
525  
530  
535  
540  
545  
550  
555  
560  
565  
570  
575  
580  
585  
590  
595  
600  
605  
610  
615  
620  
625  
630  
635  
640  
645  
650  
655  
660  
665  
670  
675  
680  
685  
690  
695  
700  
705  
710  
715  
720  
725  
730  
735  
740  
745  
750  
755  
760  
765  
770  
775  
780  
785  
790  
795  
800  
805  
810  
815  
820  
825  
830  
835  
840  
845  
850  
855  
860  
865  
870  
875  
880  
885  
890  
895  
900  
905  
910  
915  
920  
925  
930  
935  
940  
945  
950  
955  
960  
965  
970  
975  
980  
985  
990  
995  
1000

Sub A<sup>5</sup> In accordance with the present invention, a fixture is fabricated from a "solid surface" material in one thermoforming process. The process uses a flat, rigid, single sheet of "solid surface" product that is heated to a uniform temperature to make it malleable. The material is then placed over a female or male mold, and formed to a predetermined shape utilizing a vacuum. The heated material is allowed to conform to the mold shape without substantial restraint, until most of the desired deformity is achieved. At that point, movement of the material becomes restricted; the balance of the desired deformity is achieved through stretching. The manufactured component is then allowed to

cool in its restrained position, until rigid. This procedure produces a flange, which provides a point at which, for example, the bowl/shower pan can subsequently be chemically welded in either a convex or concave position. After cooling, the material is removed from the mold and chemically welded to a countertop or curb assembly, in either a horizontal or a vertical plane. A supporting plate is welded at the desired drain location. A drain hole is then machined at the drain location to accommodate the drain hardware.

It is an object of the present invention to provide an improved process for fabricating household fixtures of simulated stone or of substantially solid colors.

It is another object of this invention to provide a one piece method for manufacturing fixtures of simulated stone or of substantially solid colors.

## BRIEF DESCRIPTION OF THE DRAWINGS

A complete understanding of the present invention may be obtained by reference to the accompanying drawings, when considered  
5 in conjunction with the subsequent detailed description, in which:

FIGURE 1 illustrates a plan view of a mold used to fabricate a shower pan, in accordance with the method of this invention;

FIGURE 2 depicts an exploded, front view of the mold of  
10 FIGURE 1, with its component parts;

FIGURE 3 shows a front view of a center spring-loaded elevator utilized in fabricating the shower pan;

FIGURE 4 illustrates a cross-sectional view of a shower pan fabricated in accordance with the method of this invention;

FIGURE 5 depicts a plan view of the shower pan shown in  
20 FIGURE 4;

FIGURE 6 shows a perspective, exploded, schematic view of the mold and its component parts depicted in FIGURE 2; and

FIGURE 7 illustrates a schematic, sectional view of the mold and its components, shown in FIGURE 6.

For purposes of brevity and clarity, like components and elements of the apparatus of this invention will bear the same designations or numbering throughout the figures.

#### DESCRIPTION OF THE PREFERRED EMBODIMENT

15 *Sub A6* Generally speaking, the invention features a thermoforming method of fabricating a fixture comprising a single sheet of "solid surface" material. The sheet is heated to a uniform temperature to make it malleable. The malleable material is then placed over a female or male mold, and formed to the shape of the fixture, utilizing a vacuum. The heated material is then allowed to conform to the mold shape without significant restraint, until the desired deformity is substantially achieved. At that point, movement of the material



becomes restricted; the balance of the desired deformity is achieved through stretching. The manufactured fixture is then allowed to cool in its restrained position, until rigid.

5            Now referring to FIGURES 2, 6, and 7, the mold fixture components 10 used in the fabrication of a shower pan 18, as shown in FIGURES 4 and 5, in accordance with the present invention, is illustrated. The mold components used in the thermoforming process of the invention, comprise a medium density fiberboard (MDF) mold 12, that is attached at its center hole 14 to a vacuum providing conduit 16. It should be understood that other easily shaped and non-heat retentive materials can be used in place of or in conjunction with MDF material. The shower pan 18 or other fixture is thermoformed using a single sheet 18a of "solid surface" material. The fixture that can be fabricated by the process can comprise a bowl (including but not limited to toilets, tubs, basins, etc.), sink, tray, birdbath, shower pan, etc., or any other article requiring the forming of a depression or projection in a "solid surface" material that can hold a liquid.

The inventive method comprises the following steps:

*Sub A?* → Step 1: A single sheet of "solid surface" material 18a (FIGURE 2) is cut to a desired size that corresponds to the size of the shower pan or other product that is to be fabricated.

Step 2: The piece of material 18a is placed into a heating device (oven) to raise the temperature of the piece to a desired thermoforming temperature, the temperature gradient being in the approximate range of between 280°F - 355°F. In accordance with certain "solid surface" material manufacturers' instructions, the material may be annealed prior to and/or after performing step 2.

The piece of material being used to form the bowl/shower pan is heated for a period dependent upon its thickness. For example, 1/8" of SSV™ material is heated for a minimum of 6 minutes within the aforementioned temperature range. The sheet material 18a can remain for an indefinite period in this heated state, until the operator is ready to remove it, place it in the mold 12, and apply a vacuum 16 to the mold 12.

The oven used can be any one of various types that are commercially available. A convection oven, a heated platen oven, or a gas oven can be used to achieve the desired formability.

5 *Sub A8* A typical "solid surface" material includes an acrylic plastic with a filler of alumina trihydrate of 20 to 85% by weight. The material is manufactured under the various trade names including but not limited to: Wilsonart®, Gibraltar®, SSV™, and Dupont Corian®. Typical material thicknesses useful for thermoforming in accordance with the method of this invention, include 1/8", 1/4", 3/8" and 1/2".

10  
15 Step 3: Once heated to the desired temperature, the material 18a is malleable, and is placed into position over the three-dimensional mold 12. A retention or slip ring 15 is then placed over and surrounding the periphery of the heated piece 18a to be formed.

20 *Sub A9* Step 4: An appropriate amount of vacuum is then gradually applied, with only the weight of the retention ring 15 resting upon the material. The material 18a is vacuum formed into the mold 12, to a point of substantial deformity. The deformity is virtually unrestricted by pressure around its perimeter. When the substantially desired

deformity is attained, full pressure is applied to the retention ring 15. Full pressure causes the top of the shower pan flange portion 11, shown in FIGURE 5, to remain flat and wrinkle free. The deformity of the material should occur slowly (approx. 5-10 sec.) in order to prevent excessive stretching of the material. Excessive stretching is not desirable, because it results in "whiting" at the edges and corners. Excessive stretching is also undesirable aesthetically and, additionally, may weaken the material.

Step 5: Both the retention ring 15 and the vacuum restrain the deformed piece of "solid surface" material 18a until it cools to the point where it will retain its shape. This is dependent on the temperature to which it has been heated, the thickness of the material used, and ambient temperature.

Step 6: The pressure is removed. The vacuum is turned off and the final deformed and shaped material 18a is removed from the mold 12.

Sub A<sup>10</sup> A frame 17 (e.g., wooden, metal, etc.) is used to hold the retention ring 15 in place. This procedure produces a flange 11, as



becomes too high. At this point, the vacuum veins 12a (FIGURE 1) act as a bleeder point between the mold 12 and the "solid surface" material 18a, which allows air remaining between the mold 12 and the "solid surface" material 18a to be fully evacuated. When the molding process is complete, and at the time the counter-top or curb is welded to the flange 11, a drain plate 19 is placed under hole 20 to complete the shower base product 18 (FIGURE 4).

Since other modifications and changes varied to fit particular operating requirements and environments will be apparent to those skilled in the art, the invention is not considered limited to the example chosen for purposes of disclosure, and covers all changes and modifications which do not constitute departures from the true spirit and scope of this invention.

Having thus described the invention, what is desired to be protected by Letters Patent is presented in the subsequently appended claims.

What is claimed is: